

CLASSIFICATION

EN ISO 21952-A : G MoSi
ISO 14341-A : G2Mo
WS A5.28: ER70S-A1 (ER80S-G*)

(*) Nearest classification

GENERAL DESCRIPTION

It is a low alloyed GMA welding wire, used for the welding creep resistant 0.5 % Mo steels and fine grained steels. It gives a weld metal that is used in operating temperatures between -40°C and 500°C. It is used in the welding of steel construction applications, boiler and pressure vessels, gas pipes and turbin rotors. Industry: Ship building, heavy machinery, petro-chemical, power generation, metal fabrication industry.

CHEMICAL COMPOSITION (W%) TYPICAL, WIRE

C	Si	Mn	Mo	Cr	Cu
0.085 - 0.09	0.60 - 0.70	1.15 - 1.20	0.50	< 0.15	< 0.25

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Yield Strength	: 530 N/mm ²
Tensile Strength	: 640 N/mm ²
Elongation (L=5d)	: 27 %
Impact (ISO-V)	: 150 J (+20°C) 90 J (-20°C)

SHIELDING GASES (ISO 14175 / EN 439)

MAG : M21 - Ar + 5-25% Co₂
C1 - Co₂ (100%)

Current Type and Polarity : DC (+)

MATERIALS TO BE WELDED

	DIN	EN
Fine Grained Steels	StE 255 - StE 460 ; WStE 255 - WStE 460 -	S255N - S460N ; P255NH - P460NH S275ML ; S355M - S420M
Pipe Materials	StE 320.7 - StE 415.7 StE 360.7 TM - StE 480.7 TM X52, X56, X60, X65 (API 5LX)	L320 - L415NB L360MB - L485MB -
Boiler and Pressure Vessel Steels	15Mo3, 17Mn4, 19Mn6 22Mo4, 20MnMoNi55	16Mo3, P295GH, P310GH -
Elevated Temperature Steels	St 35.8 - St 45.8	P235G1TH - P255G1TH
Cast Steels	GS-45, GS-52, GS-60 -	GE240, GE260, GE300 G20M05
Creep Resistant Steels	17MnMoV6-4, 15NiCuMoNb5 -	- 20MnMoNi4-5

PACKING AND DIAMETER INFORMATIONS

Diameter	0.8	1.0	1.2	1.6	2.0	2.4	3.2	Spool Weight
MIG/MAG Wire	X	X	X	-	-	-	-	15 kg

Liability : All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance.

Fumes : Consult information on Welding Safety Sheet, available upon request.

Lion International U.K (M.E.) Limited

Monomark House, 27 Old Gloucester Street, London WC1N 3XX, United Kingdom.
T: +44 20 74198760 F: +44 20 78319489 E: info@lionintweld.co.uk

Lion International Middle East FZC

P.O. Box 41654, W/H No. 1K-01/4, Hamriyah Free Zone, Sharjah, UAE.
T: +971 6 5260461 F: +971 6 5260561 E: info.me@lionintweld.co.uk